SPECIFICATION CONTROL DRAWING

CHEMINAX

.064

± .003

149

77 OHM, AWG 22, 19 STRANDS OF AWG 34, DATA BUS CABLE

Date	11-2-07
Destrice	0

7722D0911

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

CONSTRUCTION DETAILS

ELECTRICAL CHARACTERISTICS

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE

DESIGNATED.

CHARACTERISTIC IMPEDANCE

77 ± 5 Ohms, Method C at 1 MHz

MUTUAL CAPACITANCE

30.0 pF/ft. (maximum)

ATTENUATION

1.0 dB/100 ft. (maximum) at 1 MHz



DIELECTRIC

SHIELD

AWG 36,

Tin-Coated Copper

Radiation-Crosslinked, Modified ETFE

Color - Light Blue/White

ADDITIONAL REQUIREMENTS

COMPONENT WIRE PRIOR TO CABLING (Test Procedures per SAE AS22759)

CROSSLINK PROOF 300 ± 3°C for 1 hour, .750 inch mandrel, .500 lb., 2.5 kV dielectric test

INSULATION (DIELECTRIC)

ELONGATION 50% (minimum) TENSILE STRENGTH 5000 lbf/in2 (minimum)

INSULATION FLAWS

SPARK TEST 3.0 kV (rms) **IMPULSE TEST** 8.0 kV (peak)

5000 megohms for 1000 ft. (minimum) INSULATION RESISTANCE LOW TEMPERATURE-COLD BEND -65 ± 3°C for 4 hours, .750 inch mandrel,

1.00 lb., 2.5 kV dielectric test

SHRINKAGE 200 ± 3°C for 1 hour,

.125 inch (maximum) in 12 inches

FINISHED CABLE

CABLE LAY LENGTH SHIELD COVERAGE **VOLTAGE WITHSTAND** (DIELECTRIC)

.75 inch (minimum), 1.25 inches (maximum)

90% (minimum) 1500 volts (rms)

WEIGHT 18.2 lbs/1000 ft. (nominal)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

The TE logo, Tyco Electronics, Cheminax and Raychem are trademarks.

